EFFECT OF CATIONIC BIO POLYMER ON CALCIUM CARBONATE CRYSTALLIZATION BY MICROBE

Nawarathna, T.H.K.^{1*}, Nakashima, K.² and Kawasaki, S.²

¹ Graduate School of Engineering, Hokkaido University, Japan

² Faculty of Engineering, Hokkaido University, Japan

* Corresponding Author: th.nawarathna@gmail.com

Formation and deposition of the mineral upon an organic matrix is referred as bio-mineralization. Organic matrix provides a structural framework for the nucleation and growth of the minerals which is mainly consists with the macro molecules like protein and polysaccharides [1]. In this current study, effect of the cationic biopolymer on the CaCO3 crystallization was analyzed by using microbial induced carbonate precipitation method. Poly-L-lysine was used as cationic biopolymer and the chemical structure of the poly-L-lysine is given in Fig. 1. Calcium carbonate was precipitated by the hydrolysis of the urea using ureolytic bacteria Pararhodobacter sp in the presence of Ca2+ ions. Experiments were conducted with and without adding bio-polymer for different bacteria concentrations and the effect of the poly-L-lysine concentration on the CaCO3 crystallization was measured by varying the poly-L-lysine concentrations and morphology of the crystals were analyzed by using Scanning Electron Microscope (SEM). Figure 2 shows the variation of the amount of precipitate with the bacteria concentration with and without poly-L-lysine. In both of the cases, amount of the precipitate increases with the bacteria concentration. Poly-L-lysine gave higher amount of precipitate compared with that without poly-L-lysine. According to the SEM images, good rhombohedral crystals were obtained for the lower bacteria concentrations and for higher bacteria concentrations combination of rhombohedral crystals were obtained. In the presence of poly-L-lysine, morphology of the crystals changed to ellipsoidal crystals and XRD results confirmed that these crystals are entirely calcite. Relationship between the amount of precipitate and the poly-L-lysine concentration is bell shaped and the morphology changed from the polyhedron type crystals to agglomeration of ellipsoidal shaped crystals. Poly-L-lysine has a significant effect on CaCO₃ crystallization and its morphology.

$$\begin{array}{c|c}
 & O \\
 & H \\
 & CH - C \\
 & CH_2 \\$$




Fig. 1 Structure of the poly-L-lysine

Fig. 2 Variation of the CaCO₃ precipitate with the bacteria concentartion in the presence of poly-L-lysine

References

[1] Xie, A.J., Shen, Y.H., Zhang, C.Y., Yuan, Z.W., Zhu, X.M. and Yang, Y.M. "Crystal growth of calcium carbonate with various morphologies in different amino acid systems", Journal of crystal growth, Vol. 285,2005, pp.436-443.